11/2004 Version

Lightleader Co.,Ltd.
No.69,zhongmensi Street,
Beijing,102300,China,
Internet: http://www.lightlead.com

Direct Tel:+8610-5166-5627
Tel: +8610-5166-5647-Ext.1
Fax:+8610-5166-5647-Ext.2
email:info@lightlead.com

Product Data Sheet

Model No.	YG-1F
Product Group	Photoluminescent long afterglow pigment
Application	Yarns,fibre/fiber, inject-printer ink,nail polish,tattoo,etc.

Typical chemical properties

Composition	Alkaline earth aluminate
Insoluble in	Alkalies,organic solvents
Decomposition by	Water,acids

Typical physical properties

Body color	Offwhite
Glowing color	Yellow-green
Specific gravity	3.1 g/cm3
Average particle size	5 μm (under 1200 meshes)

Typical luminescent properties

Excitation	Sunlight,UV radiation
Reference criterion to DIN 67510,part 1	140/22-1900-W-K

Typical decay curve



Typical luminance according to DIN 67510, part 1(mcd/m2)	
After 1 minutes	940
After 5 minutes	260
After 10 minutes	140
After 30 minutes	48
After 60 minutes	22
After 120 minutes	9

Typical excitation (left) and photoluminescence spectra (right)



Lightlead

This information is based on our present state of knowledge and is intended to provide general notes on our products and their application. It should not therefore be construed as guaranteeing specific properties of the described or their suitability for a particular application. Any existing industrial property rights must be observed. The quality of our products is guaranteed under our General Conditions of Sale.